

MDF Mouldings Technical Specifications

TECHNICAL CHARACTERISTICS

IDENTIFICATION AND CLASSIFICATION	NORM	SYMBOL	SPECIFICATION
Substrate type			Medium-density fibreboard (MDF).
Average density			600 kg / m³
SURFACE AND MECHANICAL RESISTANCE	NORM	SYMBOL	SPECIFICATION
Resistance to surface liquids	UNE-EN 12720:2009+A1:2014		Acetic acid 5% ≥ 3 Alcohol 96% ≥ 3 Oil ≥ 3
BEHAVIOUR UNDER HUMID CONDITIONS	NORM	SYMBOL	SPECIFICATION
Thickness swelling	UNE-EN 13329:2023		≤ 15 %

ENVIRONMENTAL INFORMATION

ENVIRONMENTAL PROPERTIES	NORM	SYMBOL	SPECIFICATION
Environmental certification	PEFC ST 2002:2020		Certificate: AEN-PEFC-COC-0332
Formaldehyde emissions	UNE-EN ISO 12460-3:2024 UNE-EN 717-1		Class E0,5

FINAL DECLARATION

To cut the skirting boards, use a hand saw or a power saw fitted with a fine-tooth blade.
When using a power tool, prevent the blade from overheating, as this may affect the appearance of the finish.

Before using products containing solvents, alcohol or acetone, test them on an inconspicuous area, as they may cause surface deterioration and loss of gloss.

The declared performance values have been determined in accordance with the standards specified above.
For installation and maintenance conditions, please refer to the manufacturer's current technical instructions.